



Undercoat MULTIKONTAKT 10L



Manufacturer	
Weight	12.00 kg
Product Code	MULTIKONTAKT
EAN	5904922284102
SKU	000926
Advice IBB	
Application	On all kinds of surfaces, including difficult ones
IBB ID	10338

Product specification

Manufacturer	PIGMENT Spółka Jawna	Unit	bucket
EAN	5904922284102	Atest	NIZP-PZH
Norm	PN-C-81906:2003		

Multi-contact
PRIMER - FOR DIFFICULT SUBSTRATES.

DESTINY:

The primer is a priming and bonding bridge to all types of substrates, including difficult substrates (impeding permanent bonding of the topcoat coating), such as: smooth concrete, glass, plastic, galvanized steel, tiles, old oil coatings (alkyd, phthalic) and all kinds of mineral substrates (concrete, bricks, gypsum, mineral and polymer plasters), drywall, as a primer for surface dispersion paints (emulsion, acrylic, latex, enamels and water-based epoxy paints by Pigment). It is also suitable for self-leveling floors (screeds) (diluted with 3 parts of Multikontakt and 2 parts of water) and adhesives, mineral and polymer plasters, putties. It is characterized by high adhesion to most surfaces. It significantly reduces the consumption of topcoat paint, increases adhesion, strengthens the load-bearing capacity, unifies the absorbency and consistency of the substrate.

SURFACE PREPARATION AND APPLICATION:

The product is ready for use, the contents of the package should be mixed before use. In case of thickening, up to 5% of water can be added. Before deciding to dilute, mix thoroughly. After diluting with water, make a trial painting. Due to the various properties of the substrate, tests should be carried out on smaller surfaces before application. The substrate should be dry, free from dust, dirt, oil, grease, paint residues, lichen, moss, algae and mold. All loose, not properly bonded layers should be removed. Sanding smooth surfaces significantly increases the adhesion. For degreasing, Sulfanol A by Pigment is recommended, which should be thoroughly rinsed after degreasing.

Apply with a brush, roller or spray. Fresh cement-lime plaster can be painted no earlier than 3-4 weeks after application. Fill cracks and cracks - with cement mortar. The next layers can be applied 24 hours after priming.

NOTES:

Due to the variety of technologies and raw materials used in products by other manufacturers, the manufacturer is not responsible for the consequences of mixing its product with other products. The paint should be stored in its original and

tightly closed packaging. Before putting the room into operation, ventilate the room until the odor disappears. Keep away from children. In case of eye contamination, rinse with plenty of water. In case of eye irritation or swallowing, immediately seek medical advice, show the packaging or label.

Description

paint: with a roller, brush or after appropriate dilution with spray

use and store at $+ 5 \div 25^{\circ} \text{C}$

drying time, depending on the substrate and environmental conditions: approx. 24 hours. (at 20°C and 55% relative air humidity)

application of the next layers: after 24 hours (at 20°C and 55% relative air humidity)

recommended number of layers: 1

consumption: approx. $8 \text{ m}^2 / \text{l}$

density according to PN-82 / C-81551: about $1.15 \text{ g} / \text{cm}^3$

washing tools and diluting: water

standard: PN-C-81906: 2003

warranty: 12 months from the production date (shown on the cover)

cat. A / g / FW , the permissible VOC content for this category is $30 \text{ g} / \text{l}$. The paint contains $<30 \text{ g} / \text{l}$

packaging: 1 l; 5 l; 10 l.